

High-current-density pulsed electron emission from ferroelectric discs

High-current-density pulsed electron emission from ferroelectric materials is of much current interest due to its several advantageous features and a variety of potential applications. Lead zirconium titanate (PZT) and lead lanthanum zirconium titanate (PLZT) ceramics are the two most widely used materials for this purpose. Electron emission occurs due to polarization switching in ferroelectric materials. This is done in two ways, viz., 1) application of a high-voltage (HV) pulse across the two surfaces of a disc of ferroelectric material and 2) pulsed-laser irradiation of one of the end surfaces. The former method is referred to as field excited electron emission (FEEE) and the latter one as laser induced electron emission (LIEE).

Electron-emission pulses with a peak current density of the order of tens to hundreds of A / cm^2 and duration ranging from ~ 100 ns to ~ 1 μs have been observed in the presence of a DC extraction field. Self-emission of electrons (i.e. without a DC extraction field) has also been observed. The high-current-density electron emission is understood to be plasma assisted emission, which is formed on the ferroelectric surface either due to the high electric field generated during polarization switching of the sample or due to occurrence of dielectric surface flashover.

In the case of LIEE, laser pulse durations ranging from 140 fs to 5 ns have been used. In contrast to this, in almost all the studies on FEEE from ferroelectric discs reported in the literature, HV excitation pulses of duration exceeding 100 ns were applied. This was considered to be necessary to achieve a high degree of polarization reversal in the ferroelectric sample, having polarization switching time of this order. However, use of HV excitation pulses of a few ns duration is desirable for the purpose of achieving unipolar excitation and to improve stability / lifetime of the ferroelectric cathodes.

At Laser Plasma Laboratory, we have been involved in experimental studies of electron emission ferroelectrics. In order to study the feasibility of electron emission using short duration high voltage excitation pulses, investigations were carried out on poled ferroelectric ceramic disks. Electron emission was observed from the surface toward the positive end of the polarization vector (i.e. the one with the surface screening electrons) by applying a 6ns of HV excitation pulse either on the rear surface or on the front emitting surface, keeping the other surface at ground potential. Pulsed electron emission occurred with a current density ~ 400 - $450 A / cm^2$ and FWHM duration of ~ 200 - 250 ns in the presence of a DC extraction field. Self-emission of electrons with a current density of ~ 20 - $30 A / cm^2$ was also observed for both the configurations of application of the excitation pulse. The electron emission is understood to result from occurrence of partial polarization reversal

in the ferroelectric sample followed by plasma formation on its surface. These observations bring out the usability of short duration (few ns) HV excitation pulses for FEEE from ferroelectric materials.

References :

- 1) High current density electron emission from PZT ferroelectric disc under application of short duration voltage pulses
A.Moorti, P.A.Naik, and P.D.Gupta
IEEE Tr. Plasma Science 32, 256, 2004

- 2) Laser driven high current density pulsed electron emission from lead zirconium titanate (PZT) ferroelectric ceramic.
A.Moorti, S.Sailaja, P.A.Naik, P.D.Gupta, Yu.V.Korobkin, I.V.Romanov,
A.A.Rupasov and A.S.Shikhanov
Applied Physics Letters, 79, 1163, 2001